



**ALPHA & OMEGA**  
SEMICONDUCTOR

# ***Alpha & Omega Semiconductor Product Reliability qualification Report***

**AK10 series**, rev A

**Plastic Encapsulated Device**

**ALPHA & OMEGA Semiconductor, Inc**

**[www.aosmd.com](http://www.aosmd.com)**

This AOS product reliability report summarizes the qualification result for AK10 series. Accelerated environmental tests are performed on a specific sample size, and then followed by electrical test at end point. Review of final electrical test result confirms that AK10 series passes AOS quality and reliability requirements. The released product will be categorized by the process family and be routine monitored for continuously improving the product quality.

## I. Reliability Stress Test Summary and Results

Test Item	Test Condition	Time Point	Total Sample Size	Number of Failures	Reference Standard
HTRB	Temp = 150°C , VR=80% of VRmax	1000 hours	22 pcs	0	JESD22-A108
HTSL	Temp = 150°C	1000 hours	22 pcs	0	JESD22-A103
Solderability Test	Temp = 245°C	5 seconds	5 pcs	0	JESD22-B102
RSH	Temp = 260°C	10 seconds	5 pcs	0	JESD22-B106

**Note:** The reliability data presents total of available generic data up to the published date.

## II. Reliability Evaluation

**FIT rate (per billion): 160.25**

**MTTF = 712 years**

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size. Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

**Failure Rate** =  $\text{Chi}^2 \times 10^9 / [2 (N) (H) (Af)] = 160.25$

**MTTF** =  $10^9 / \text{FIT} = 712 \text{ years}$

**Chi<sup>2</sup>** = Chi Squared Distribution, determined by the number of failures and confidence interval

**N** = Total Number of units from burn-in tests

**H** = Duration of burn-in testing

**Af** = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and Tuse = 55°C)

Acceleration Factor [**Af**] =  $\text{Exp} [Ea / k (1/Tj u - 1/Tj s)]$

**Acceleration Factor ratio list:**

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
<b>Af</b>	<b>259</b>	<b>87</b>	<b>32</b>	<b>13</b>	<b>5.64</b>	<b>2.59</b>	<b>1</b>

**Tj s** = Stressed junction temperature in degree (Kelvin),  $K = C + 273.16$

**Tj u** = The use junction temperature in degree (Kelvin),  $K = C + 273.16$

**k** = Boltzmann's constant,  $8.617164 \times 10^{-5} \text{ eV} / \text{K}$

**AK10 series Part No. can refer to below table**

AK10-033C	AK10-058C	AK10-066C	AK10-076C	AK10-100C
AK10-170C	AK10-190C	AK10-240C	AK10-270C	AK10-320C
AK10-380C	AK10-430C	AK10-470C		