

AOS Semiconductor Product Reliability Report

AO4443, rev B

Plastic Encapsulated Device

ALPHA & OMEGA Semiconductor, Inc

495 Mercury Drive Sunnyvale, CA 94085 U.S.

Tel: (408) 830-9742 www.aosmd.com



This AOS product reliability report summarizes the qualification result for AO4443. Accelerated environmental tests are performed on a specific sample size, and then followed by electrical test at end point. Review of final electrical test result confirms that AO4443 passes AOS quality and reliability requirements. The released product will be categorized by the process family and be monitored on a quarterly basis for continuously improving the product quality.

Table of Contents:

- Product Description
- II. Package and Die information
- III. Environmental Stress Test Summary and Result
- IV. Reliability Evaluation

I. Product Description:

The AO4443 uses advanced trench technology to provide excellent RdS(ON), and ultra-low low gate charge. This device is suitable for use as a load switch or in PWM applications.

- RoHS Compliant
- Halogen Free

Detailed information refers to datasheet.

II. Die / Package Information:

AO4443

Process Standard sub-micron

Low voltage P channel

Package Type 8 leads SOIC

Lead FrameCuDie AttachAg EpoxyBonding WireCu wire

Mold Material Epoxy resin with silica filler MSL (moisture sensitive level) Level 1 based on J-STD-020

Note * based on information provided by assembler and mold compound supplier



III. Result of Reliability Stress for AO4443

Test Item	Test Condition	Time	Lot	Total	Number	Standard
		Point	Attribution	Sample	of	
				size	Failures	
MSL	168hr 85℃	-	29 lots	3575pcs	0	JESD22-
Precondition	/85%RH +3 cycle reflow@260℃					A113
HTGB	Temp = 150 °c,	168hrs		77pcs	0	JESD22-
	Vgs=100% of	500 hrs		•		A108
	Vgsmax	1000 hrs	1 lot			
			(Note A*)	77pcs / lot		
HTRB	Temp = 150 °c,	168hrs		77pcs	0	JESD22-
	Vds=80% of	500 hrs				A108
	Vdsmax	1000 hrs	1 lot			
			(Note A*)	77pcs / lot		
HAST	130 +/- 2°c,	100 hrs	16 lots	880pcs	0	JESD22-
	85%RH, 33.3 psi,					A110
	Vgs = 100% of		(31.4.43)	55 (1		
	Vgs max	1001	(Note A*)	55 pcs / lot		150500
Pressure Pot	121°c, 29.7psi,	96 hrs	20 lots	1100pcs	0	JESD22-
	RH=100%					A102
			(Note A*)	55 pcs / lot		
Temperature	-65°c to 150°c,	250 / 500	29 lots	1595pcs	0	JESD22-
Cycle	air to air	cycles				A104
			01 4 00	,		
			(Note A*)	55 pcs / lot		

Note A: The reliability data presents total available generic data up to the published date.

IV. Reliability Evaluation

FIT rate (per billion): 23 MTTF = 4957 years

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size of the selected product (AO4443). Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

Failure Rate = $\text{Chi}^2 \times 10^9 / [2 \text{ (N) (H) (Af)}] = 1.83 \times 10^9 / [2x2x77x1000x258] = 23 \text{ MTTF} = <math>10^9 / \text{FIT} = 4.34 \times 10^7 \text{hrs} = 4957 \text{ years}$

Chi² = Chi Squared Distribution, determined by the number of failures and confidence interval

N = Total Number of units from HTRB and HTGB tests

H = Duration of HTRB/HTGB testing

Af = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and Tuse = 55°C)

Acceleration Factor [Af] = \mathbf{Exp} [Ea / k (1/Tj u - 1/Tj s)]

Acceleration Factor ratio list:

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
Af	258	87	32	13	5.64	2.59	1

Tj s = Stressed junction temperature in degree (Kelvin), K = C+273.16

Tj u = The use junction temperature in degree (Kelvin), K = C+273.16

 $K = Boltzmann's constant, 8.617164 \times 10^{-5} eV / K$