



**ALPHA & OMEGA**  
SEMICONDUCTOR

# ***AOS Semiconductor Product Reliability Report***

**AO4496,** rev C

**Plastic Encapsulated Device**

**ALPHA & OMEGA Semiconductor, Inc**

**[www.aosmd.com](http://www.aosmd.com)**

This AOS product reliability report summarizes the qualification result for AO4496. Accelerated environmental tests are performed on a specific sample size, and then followed by electrical test at end point. Review of final electrical test result confirms that AO4496 passes AOS quality and reliability requirements. The released product will be categorized by the process family and be monitored on a quarterly basis for continuously improving the product quality.

## Table of Contents:

- I. Product Description
- II. Package and Die information
- III. Environmental Stress Test Summary and Result
- IV. Reliability Evaluation

## I. Product Description:

The AO4496 uses advanced trench technology to provide excellent  $R_{DS(ON)}$  with low gate charge. This device is suitable for use as a DC-DC converter application.

- RoHS Compliant
- Halogen Free

Detailed information refers to datasheet.

## II. Die / Package Information:

	<b>AO4496</b>
<b>Process</b>	Standard sub-micron 30V N-Channel MOSFET
<b>Package Type</b>	SO8
<b>Lead Frame</b>	Cu
<b>Die Attach</b>	Ag epoxy
<b>Bonding</b>	Cu wire
<b>Mold Material</b>	Epoxy resin with silica filler
<b>MSL (moisture sensitive level)</b>	Level 1 based on J-STD-020
<b>Note</b>	* based on information provided by assembler and mold compound supplier

### III. Result of Reliability Stress for AO4496

Test Item	Test Condition	Time Point	Lot Attribution	Total Sample size	Number of Failures	Standard
MSL Precondition	168hr 85°C /85%RH +3 cycle reflow@260°C	-	33 lots	5489pcs	0	JESD22-A113
HTGB	Temp = 150 °c, Vgs=100% of Vgsmax	168hrs 500 hrs 1000 hrs	4 lot 6 lot 5 lot (Note A*)	1155pcs  77pcs / lot	0	JESD22-A108
HTRB	Temp = 150 °c, Vds=80% of Vdsmax	168hrs 500 hrs 1000 hrs	4 lot 6 lot 5 lot (Note A*)	1155pcs  77pcs / lot	0	JESD22-A108
HAST	130°C, 85%RH, 33.3 psi, Vgs = 100% of Vgs max	96 hrs	20 lots  (Note A*)	1100pcs  55 pcs / lot	0	JESD22-A110
Pressure Pot	121°C, 29.7psi, RH=100%	96 hrs	24lots  (Note A*)	1848pcs  77 pcs / lot	0	JESD22-A102
Temperature Cycle	-65°C to 150°C, air to air	250 / 500 cycles	33 lots  (Note A*)	2541pcs  77 pcs / lot	0	JESD22-A104

**Note A:** The reliability data presents total of available generic data up to the published date.

### IV. Reliability Evaluation

**FIT rate (per billion): 3**

**MTTF = 42987 years**

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size of the selected product (AO4496). Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

$$\text{Failure Rate} = \text{Chi}^2 \times 10^9 / [2 (N) (H) (Af)]$$

$$= 1.83 \times 10^9 / [2 \times (8 \times 77 \times 168 + 16 \times 77 \times 500 + 10 \times 77 \times 1000) \times 258] = 3$$

$$\text{MTTF} = 10^9 / \text{FIT} = 3.77 \times 10^8 \text{hrs} = 42987 \text{ years}$$

**Chi<sup>2</sup>** = Chi Squared Distribution, determined by the number of failures and confidence interval

**N** = Total Number of units from HTRB and HTGB tests

**H** = Duration of HTRB/HTGB testing

**Af** = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and Tuse = 55°C)

Acceleration Factor [Af] =  $\text{Exp}^{[Ea / k (1/Tj u - 1/Tj s)]}$

**Acceleration Factor ratio list:**

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
Af	258	87	32	13	5.64	2.59	1

**Tj s** = Stressed junction temperature in degree (Kelvin), K = C+273.16

**Tj u** = The use junction temperature in degree (Kelvin), K = C+273.16

**K** = Boltzmann's constant, 8.617164 X 10<sup>-5</sup>eV / K